

Technical Data Sheet

SZ3300/00 PRECATALYSED LACQUERS

Supersedes previous issue dated 05/09/2011
DATE 2/07/12

A range of matt to gloss clear, precatylased coat on coat lacquers.

Fast Drying, good durability. Suitable for self sealing/priming – no separate basecoat required.

Gloss Versions:	10% - SZ 3310 (M127) 30% - SZ 3330 (M703) 35% - SZ 3335 (M838) 60% - SZ 3360 (N818) 90% - SZ 3390 (P009)
Area of use:	All furniture types.
Method of use:	Conventional, airless and airmix spray guns.
Mixing procedure:	Ready for use. Use DSG 34 / Number 34 Thinners thinners if required.

Technical Characteristics

Solids content (%):	22 ± 1
Specific gravity (kg/l):	0.900 ± 0.030
Viscosity (DIN 4 at 20°C) seconds:	26 ± 2

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.

Temperature for use	15-30°C	
Recommended application weight (g/m ²):	Minimum 80, Maximum 140	
Drying time (60 g/m ² at 20°C):	Dust free	10 min
	Touch dry	25 min
	Sanding/ overcoating	1 hour
	Through dry	1.5 hours
Number of coats:	Maximum 3	
Shelf-life:	1 year	
Clean-up	DX1130	

Substrate preparation: Must be clean, dry, and finish sanded. Substrate should be free of grease, oil, dirt, fingerprints, and any contamination to ensure optimum adhesion and coating performance properties.

Special instructions

Stir well before use.

Warning

Read the separate Health and Safety sheet prior to use. This is just one of a wide range of industrial wood coatings from Sherwin Williams. Should you require any further information on this, or any other product within our range, simply contact us at the address below.

N.B.: DATA PROVIDED ON THIS TECHNICAL DATA SHEET CORRESPOND TO OUR BEST KNOWLEDGE AND EXPERIENCE. WE ASSURE CONSISTENCY ON THE CHEMICAL-PHYSICAL CHARACTERISTICS OF OUR PRODUCTS, WITHIN THE TOLERANCE LIMITS SPECIFIED ON OUR TECHNICAL DATA SHEETS. RESPONSIBILITY OF FINAL RESULT OF PRODUCT APPLICATION IS FULLY UP TO THE USERS, WHO SHALL MAKE SURE THAT THE PRODUCT CORRESPONDS TO THEIR OWN NEEDS WITH REGARD TO APPLICATION SYSTEM, TO SUBSTRATES USED AS WELL AS TO WORKING CONDITIONS.

WARNING: ACTUAL VISCOSITY OF SOME PIGMENTED AND/OR THIXOTROPIC PRODUCTS MAY DIFFER FROM THE VISCOSITY SHOWN ON THE TECHNICAL DATA SHEET. DIFFERENCES ARE TO BE REGARDED AS ACCEPTABLE IF WITHIN 30% MAXIMUM.